



NICROBRAZNEWS

SEPTEMBER 2024

Nicrobraz® Cement, Thinner, and 'S' Binder™ Shelf Life

Nicrobraz® 320, 520, 620, 1020 Cements and Thinners



A minimum shelf life of 24 months is given for these products. To ensure safe storage the containers should be inspected periodically. If the cement becomes hard at room temperature, or becomes water thin, it will not function as required to support the brazing filler metal and should be discarded. These products can be used after the minimum 24 month shelf life if they have not dried out or broken down.

If the integrity of the can is compromised, evaporation of solvent can occur. Evaporation will create an unsafe condition and affect the viscosity of the products causing them to thicken. In this case we recommend the use of the appropriate Nicrobraz® Cement Thinner to achieve the desired viscosity.

Nicrobraz® Cement Thinners are subject to the same 24 month shelf life as the Cements.

Nicrobraz® 650

A minimum shelf life of 3 months is given for Nicrobraz® 650.

Nicrobraz® 680

A minimum shelf life of 12 months is given for Nicrobraz® 680.

Nicrobraz® 'S' Binder™

A minimum shelf life of 24 months is given for Nicrobraz® 'S' Binder™. If the 'S' Binder™ becomes hard at room temperature, or becomes water thin, it will not function as required to support the brazing filler metal and should be discarded.

Nicrobraz® Cements & 'S' Binder™

To prolong storage life, these products should be kept in a tightly sealed container, in a cool area. Do not allow the product to freeze, as this may affect viscosity.

Nicrobraz® Cements	Minimum Shelf Life
Nicrobraz® 320, 520, 620, 1020 & Thinners	24 months
Nicrobraz® 650	3 months
Nicrobraz® 680	12 months

Nicrobraz® 'S' Binder™	Minimum Shelf Life
Nicrobraz® 'S' Binder™	24 months



WALLCOLMONOY
HI TEMP BRAZING ALLOYS

NICROBRAZNEWS

Note:

A minimum shelf life is given for these products, and is provided only to give a guideline to follow. It is not our intention to indicate that these products will not be usable after that date. Many of our customers have used these products satisfactorily, well beyond the minimum shelf life date. Refer to Wall Colmonoy SDSs for important safety information.

For more information, please contact:

WORLD HEADQUARTERS

WALL COLMONOY CORP. (USA)

101 W. Girard

Madison Heights, MI 48071

Tel: 248-585-6400

Email: wcc@wallcolmonoy.com

EUROPEAN HEADQUARTERS

WALL COLMONOY LTD. (UK)

Alloy Industrial Estate

Pontardawe Swansea SA8 4HL

Tel: +44 (0) 1792 860647

Email: alloyproductsales@wallcolmonoy.co.uk

About Wall Colmonoy and Brazing The Pioneers and Today's Leading Experts

Wall Colmonoy joins parts for high-temperature and corrosion applications using Nicrobraz[®], Niferobraz[®], and CuBraz[™] brazing filler metals and brazing aids.

The pioneer of high-temperature brazing, Wall Colmonoy's expert brazing engineer, Bob Peaslee, invented a new brazing technology involving nickel-based filler metals and hydrogen atmosphere furnaces in 1950. As a result, the new filler metal, Nicrobraz[®], was created.

Today, Nicrobraz[®], Niferobraz[®], and CuBraz[™] brazing filler metals are used in a variety of industries including aerospace, oil & gas, steel, energy, food, automotive, rail and defense, meeting AWS, AMS, G.E., Honeywell, Pratt & Whitney and Rolls-Royce specifications. Nicrobraz[®] products are available as powder, paste, transfer tape, rods, and sheets in a full range of sizes and specifications. Wall Colmonoy also custom formulates brazing filler metals to meet customer specific requirements.

Copyright © 2024 by Wall Colmonoy Corporation. All rights reserved.

No part of this work may be published, translated or reproduced in any form or by any means, or incorporated into any information retrieval system, without the written permission of the copyright holder. Permission requests should be addressed to: Marketing Communications, marketing@wallcolmonoy.com

Disclaimer

Although the information presented in this work is believed to be reliable, this work is published with the understanding that Wall Colmonoy Corporation and the authors are supplying general information and are not attempting to render or provide engineering or professional services. Neither Wall Colmonoy Corporation nor any of its employees make any warrant, guarantee, or representation, whether expressed or implied, with respect to the accuracy, completeness or usefulness of any information, product, process or apparatus discussed in this work; and neither Wall Colmonoy Corporation nor any of its employees shall be liable for any losses or damages with respect to or resulting from the user of, or the inability to use, any information, product, process or apparatus discussed in this work.